

Munken Premium Cream

We are still able to read books that were printed hundreds of years ago thanks to high quality paper used. Munken Premium Cream has been inspired by that genuine quality and is intended to be kept for many future generations. Munken Premium Cream is a cream shaded, woodfree, uncoated paper with a natural surface that provides excellent readability. The paper is suitable for both black and white and 4-colour print and is ideal for all intricate, beautiful and exclusive printed matter. Munken Premium Cream comes in various bulks and grammages and is available in both sheets and reels. There is also a white shaded version: Munken Premium White. Munken Premium Cream standard products are available as FSC™ and PEFC certified.

MUNKEN PREMIUM CREAM 13 - (DEC 09)

Grammage (g/m ²)	80	90	100	115
Opacity (%)	89	90	91	93
Thickness (µm)	104	117	130	150
Bulk (thickness/grammage)				1.3
Whiteness (CIE)				62
Brightness (ISO 2470/D65 %)				80
Roughness (Bendtsen, ml/min)				300
Screen recommended 133-150 lpi				
Permanent document, acid free ISO 9706				
FSC, PEFC, ISO 14001, Paper Profile, EMAS				

MUNKEN PREMIUM CREAM 15 - (JAN 07)

Grammage (g/m ²)	80	90	100
Opacity (%)	88	90	92
Thickness (µm)	120	135	150
Bulk (thickness/grammage)			1.5
Whiteness (CIE)			62
Brightness (ISO 2470/D65 %)			80
Roughness (Bendtsen, ml/min)			300
Screen recommended 133-150 lpi			
Permanent document, acid free ISO 9706			
FSC, PEFC, ISO 14001, Paper Profile, EMAS			



The mark of
responsible forestry



Promoting sustainable forest
management
www.pefc.org



MUNKEN PREMIUM CREAM 17.5 - (JAN 07)

Grammage (g/m ²)	80	90	100 ^d
Opacity (%)	88	90	92
Thickness (µm)	140	158	175
Bulk (thickness/grammage)			1.75
Whiteness (CIE)			62
Brightness (ISO 2470/D65 %)			80
Roughness (Bendtsen, ml/min)			500
Screen recommended 100-133 lpi			
Permanent document, acid free ISO 9706			
FSC, PEFC, ISO 14001, Paper Profile, EMAS			

MUNKEN PREMIUM CREAM 19.5 - (JAN 07)

Grammage (g/m ²)	80	90	100
Opacity (%)	89	91	93
Thickness (µm)	156	176	195
Bulk (thickness/grammage)			1.95
Whiteness (CIE)			62
Brightness (ISO 2470/D65 %)			80
Roughness (Bendtsen, ml/min)			700
Screen recommended 85-133 lpi			
Permanent document, acid free ISO 9706			
FSC, PEFC, ISO 14001, Paper Profile, EMAS			

Values are targets only and can be subject to changes over time without prior notice. You will find the latest valid technical specifications and information about our products at www.arcticpaper.com.

^d Not standard production. Min. 10 tonnes and paper machine trim needed.

